

Rayoface™ ACPA

Data

High Performance, Two Side Coated Clear, High Gloss
Biaxially Oriented Polypropylene Film for Facestock Applications

FEATURES

- Dedicated superior print receptive top coating for excellent printability
- Dedicated adhesive receptive coating for enhanced adhesive anchorage
- Excellent clarity for “no label look”
- Excellent hot/cold moisture resistance
- Recyclable with polyolefin materials
- Semi-squeeze performance
- High stiffness for conversion and automatic dispensing
- Balanced biaxial orientation for superior even die cutting
- High gloss surface


PRINTABILITY

Rayoface ACPA has a proprietary top coating which gives outstanding printing performance across a wide variety of printing processes including flexography, letterpress, offset, silkscreen, gravure and hot or cold foiling processes. It is highly compatible with UV, water-based and solvent-based inks, excellent for demanding applications where the label can be exposed to moisture and a range of temperatures. However, exact ink and foil systems should be recommended by your supplier.

CONVERSION

The balanced biaxial orientation of Rayoface ACPA results in excellent die cutting performance, enhancing label edge appearance and prolonging die life. The high machine direction stiffness and tensile strength produces excellent matrix stripping and superior high speed label dispensing.

CONSTRUCTION



STANDARD ROLL SPECIFICATIONS

Film	Core Size / (in)	Approx Outside Dia / (in)	Length / (feet)
ACPA200	6	32.0	30500
ACPA230	6	34.3	30500

Alternative roll lengths/core sizes are available subject to negotiation.
The print coating is available on either the inner or outer surface of Rayoface ACPA.

Rayoface™ ACPA _____ Data

Technical Properties (Typical Values)

Physical Data

Property	Test Method	Test Conditions	Units	ACPA	
Thickness	Innovia Films test		gauge	200	230
Yield	Innovia Films test		in ² /lb g/m ²	15000 47.2	13000 54.3
Optical: Gloss	ASTM D 2457	45°	%	90	
Haze (wide angle)	ASTM D 1003	2.5°		<3.0	

Mechanical Data

Tensile strength	ASTM D 882	Strain rate 50%/min	kpsi	MD TD	29.0 26.0
Elongation at break	ASTM D 882	Strain rate 50%/min	%	MD TD	105 120
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10%/min	kpsi	MD TD	348 319

Thermal Data

Dimensional stability	Innovia Films test	60 secs at 248° F	%	MD TD	3.0
		60 secs at 266° F			MD TD

All properties are tested under standard laboratory conditions: 73 ±4° F; 50 ±5% RH, unless otherwise stated.
 MD Machine direction TD Transverse direction

Film Storage and Handling

Care should be taken to protect rolls of film from storage temperatures above 86° F and localized sources of heat above 113° F.

Rolls of Rayoface ACPA should be protected from high levels of moisture and accidental water splashes at all times. The rolls should remain in the protective coverings supplied until ready for use on converting machinery.

Converted rolls, in both master and slit roll form should be similarly protected at all times.

Rayoface ACPA is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Please refer to literature reference L110 - 1 of 2.

Food Contact

Rayoface ACPA is not suitable for applications involving direct contact with foodstuffs. For specific inquiries, please refer to literature reference L110 - 2 of 2, or contact our Technical Services Department.

Health and Safety Guidelines

For Health and Safety information, please refer to literature reference L190.

Additional Information

Innovia Films neither guarantees nor tests the pasteurization resistance for Rayoface ACPA. If this product is to be used in a pasteurizable application, we would advise you to undertake your own thorough testing to ensure it meets your requirements.



www.innoviafilms.com
 email: labelsamericas@innoviafilms.com
 ™Trademark of Innovia Films Group

Sales Offices

Americas (USA) Tel +1 877 822 3456
 Europe (UK) Tel +44 (0)16973 42281
 Asia-Pacific (Aus) Tel +61 3 9303 0600

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.