

Rayoface™ CDI Data

Clear, High Gloss, Top Coated Biaxially Oriented Polypropylene Film for Facestock Applications Requiring Indigo® ElectroInk™ Receptivity

FEATURES

- Dedicated superior print receptive top coating for excellent printability by Indigo® ElectroInk™ toner systems
- Fully certified by HP Indigo®
- Approved for WS4000/4050/4500 and WS2000 presses
- High clarity
- High gloss surface
- Excellent hot/cold moisture resistance
- Recyclable with polyolefin materials
- Semi-squeeze performance
- High stiffness for conversion and automatic dispensing
- Balanced biaxial orientation for superior even die cutting

PRINTABILITY


Rayoface CDI has a proprietary aqueous top coating specifically designed for receptivity of Indigo® liquid toners.

CONVERSION

The balanced biaxial orientation of Rayoface CDI results in excellent die cutting performance, enhancing label edge appearance and prolonging die life.

The high machine direction stiffness and tensile strength produces excellent matrix stripping and superior high speed label dispensing.

CONSTRUCTION



STANDARD ROLL SPECIFICATIONS

Film	Core Size / (in)	Approx Outside Dia / (in)	Length / (feet)
CDI200	3	19.1	10100
	6	31.7	30500
CDI230	3	20.3	10100
	6	34.1	30500

Alternative reel lengths/core sizes are available subject to negotiation.

The ElectroInk™ receptive surface is available on either the inner or outer surface of Rayoface CDI.

Indigo® and ElectroInk™ are trademarks/registered trademarks of HP Indigo®.



Rayoface™ CDI _____ Data

Technical Properties (Typical Values)

Physical Data

Property	Test Method	Test Conditions	Units	CDI	
Thickness	Innovia Films test		gauge	200	230
Yield	Innovia Films test		in ² /lb g/m ²	15300 46.1	13200 53.2
Optical: Gloss	ASTM D 2457	45°	%	90	
Haze (wide angle)	ASTM D 1003	2.5°		<3.5	

Mechanical Data

Tensile strength	ASTM D 882	Strain rate 50%/min	kpsi	MD TD	29.0 26.0
Elongation at break	ASTM D 882	Strain rate 50%/min	%	MD TD	105 120
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10%/min	kpsi	MD TD	348 319

Thermal Data

Dimensional stability	Innovia Films test	60 secs at 248 °F	%	MD TD	3.0
		60 secs at 266 °F			MD TD

All properties are tested under standard laboratory conditions: 73 ±4°F; 50 ±5% RH, unless otherwise stated.
MD Machine direction TD Transverse direction

Film Storage and Handling

Care should be taken to protect rolls of film from storage temperatures above 86 °F and localized sources of heat above 113 °F.

The rolls should remain in the protected coverings supplied until ready for use on converting machinery.

Converted rolls, in both master and slit roll form should be similarly protected at all times.

Rayoface CDI is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Please refer to literature reference L110 - 1 of 2.

Food Contact

Rayoface CDI is suitable for most applications involving direct contact with foodstuffs. For specific inquiries, please refer to literature reference L110 - 2 of 2, or contact our Technical Services Department.

Health and Safety Guidelines

For Health and Safety information, please refer to literature reference L190.



www.innoviafilms.com
email: labelsamericas@innoviafilms.com
™Trademark of Innovia Films Group

Sales Offices

Americas (USA) Tel +1 877 822 3456
Europe (UK) Tel +44 (0)16973 42281
Asia-Pacific (Aus) Tel +61 3 9303 0600

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform their own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.